

1585CW[®]-2

S H E A T H I N G T A P E



Venture Tape 1585CW-2 is a polypropylene sheathing tape coated with an aggressive acrylic pressure sensitive adhesive (PSA) designed for use as a closure system and vapor seal on all interior and exterior sheathing materials.

Venture Tape 1585CW-2 exceeds most building code requirements and can be used for new construction as well as repair on all vapor barrier materials.

Available in red and white, Venture Tape 1585CW-2 is the highest performing, highest value product on the market today.

FEATURES & BENEFITS

- High performance sheathing tape installs and performs well over a wide temperature range
- Excellent vapor barrier tape on polyethylene film
- Performs well as a seam tape on extruded foam products such as **Styrofoam[®]** and **Foamular[®]**
- Applies to all major housewraps including **Tyvek[®]** and **Typar[®]**
- Great for use as a sealing tape on **DensGlass Gold[®]** and other sheathing brands

PRODUCT CONFIGURATIONS

- 1 7/8" x 72Y 16 rolls/case
- 2 1/2" x 72Y 12 rolls/case

Contact Venture Tape today for a complete list of products or a free sample

Toll Free North America 800-343-1076
From United Kingdom 0-800-962-957
From Australia 1-800-122-797
www.venturetape.com
www.boma.it

USA

Venture Tape Corp.
30 Commerce Road
Rockland, MA 02370
781-331-5900
FAX 781-871-0065
www.venturetape.com

Europe - Venture Tape

Venture Tape Europe Corp.
Units 5 - 6, Faraday Close,
Drayton Fields, Daventry,
Northamptonshire, England NN11 8RD
(0) 1327 876555
FAX (0) 1327 876444

Europe - BOMA

BOMA s.r.l.
Via Aquileia 22/30
34070 Villesse (GO)
Italy
0481 96431 1
FAX 0481 91440

Australasia

Venture Tape Australasia, Pty., Ltd.
11B Production Drive
Campbellfield, VIC 3061
Australia
(03) 9357 6025
FAX (03) 9357 6045

Test	Typical Value	Test Method
Total Product Thickness	3.0 mils	PSTC-133
Carrier Thickness	1.5 mils	PSTC-133
Adhesive Thickness	1.5 mils	PSTC-133
Peel Adhesion - Stainless Steel	65 oz/in	PSTC-133
Peel Adhesion - Polyethylene	16 oz/in	PSTC-133
Peel Adhesion - Tyvek [®]	28 oz/in	PSTC-133
Shear Strength	>96 hours	PSTC-133
Tensile Strength	20 lb/inch width	PSTC-133
Elongation	136%	PSTC-133
WVTR	0.16 g/100 in ² /24 hr	ASTM E-96
Application Temperature	-20° F to 120° F	
Service Temperature	-40° F to 275° F	

Typical values are not intended to be used for specification development. Technical data is believed to be true and accurate; Venture Tape recommends that the purchaser test for fitness of use in all applications.

VentureTape[®]